International Application No.: PCT/JP2004/011743

U.S. Patent Application No.: Unknown

February 7, 2006

Page 3 of 6

## **AMENDMENTS TO THE CLAIMS:**

This listing of claims will replace all prior versions, and listings, of claims in the application:

## **LISTING OF CLAIMS:**

Claims 1-10 (canceled).

Claim 11 (new): A rare-earth sintered magnet, a main phase of which includes an R<sub>2</sub>T<sub>14</sub>B type compound phase, the magnet comprising:

27 mass% through 32 mass% of R, which is at least one rare-earth element that is selected from the group consisting of Nd, Pr, Tb, and Dy and that always includes at least one of Nd and Pr;

60 mass% through 73 mass% of T, which is either Fe alone or a mixture of Fe and Co:

0.85 mass% through 0.98 mass% of Q, which is either B alone or a mixture of B and C and which is converted into B on a number of atoms basis when its mass percentage is calculated;

more than 0 mass% through 0.3 mass% of Zr;

at most 2.0 mass% of an additive element M, which is at least one element selected from the group consisting of AI, Cu, Ga, In and Sn; and inevitably contained impurities.

International Application No.: PCT/JP2004/011743

U.S. Patent Application No.: Unknown

February 7, 2006

Page 4 of 6

Claim 12 (new): The rare-earth sintered magnet of claim 11, comprising substantially no accumulated phases of Q.

Claim 13 (new): The rare-earth sintered magnet of claim 11, wherein the additive element includes Ga, which accounts for 0.01 mass% through 0.08 mass% of the magnet.

Claim 14 (new): The rare-earth sintered magnet of claim 13, comprising at most 0.95 mass% of Q.

Claim 15 (new): The rare-earth sintered magnet of claim 14, comprising at least 0.90 mass% of Q.

Claim 16 (new): The rare-earth sintered magnet of claim 11, wherein the magnet has a square ratio Hk/HcJ of at least 0.9 in its demagnetization curve.

Claim 17 (new): A material alloy for a rare-earth sintered magnet, a main phase of which includes an R<sub>2</sub>T<sub>14</sub>B type compound phase, the alloy comprising:

27 mass% through 32 mass% of R, which is at least one rare-earth element that is selected from the group consisting of Nd, Pr, Tb, and Dy and that always includes at least one of Nd and Pr;

60 mass% through 73 mass% of T, which is either Fe alone or a mixture of Fe and Co;

International Application No.: PCT/JP2004/011743

U.S. Patent Application No.: Unknown

February 7, 2006

Page 5 of 6

0.85 mass% through 0.98 mass% of Q, which is either B alone or a mixture of B and C;

more than 0 mass% through 0.3 mass% of Zr;

at most 2.0 mass% of an additive element M, which is at least one element selected from the group consisting of AI, Cu, Ga, In and Sn; and inevitably contained impurities.

Claim 18 (new): The rare-earth alloy of claim 17, comprising substantially no accumulated phases of Q.

Claim 19 (new): The rare-earth alloy of claim 17, wherein the additive element includes Ga, which accounts for 0.01 mass% through 0.08 mass% of the magnet.

Claim 20 (new): The rare-earth alloy of claim 19, comprising at most 0.95 mass% of Q.